



Base Coat Adhesive

Weight: 50 lbs.

Coverage: 100 sq. ft. at 1/16" thick.

Storage: Materials must be stored off the ground and protected from direct sunlight and moisture. Storage life is one year in dry sealed bag.

Installation Mixing: Mix 50 pounds of the Vision Premium BaseCoat powder with five quarts of clean potable water (at 45° - 80°F). Add the powder to the water in the mechanical mortar mixer or slow speed drill (500-RPM maximum) with a Jiffler type paddle. Allow mix to slake for 5 minutes then remix. Add a small amount of water or powder if necessary until desired consistency is reached. Do not retemper after this point.

Working Time: Bucket Life: 5 hours

Dry Time: 24 hours at 70° F

Application: For more information regarding application, please turn to the Technical Tab or go to our website: www.rescom.com

10/19