



## ***Fiberglass Drywall Joint Tape & Wall Repair Fabric / Interior Wall Reinforcement Fabric***

**Weight (After Coat):** 2 ounce per square yard +/- .15 oz/yd<sup>2</sup> (65g/m<sup>2</sup> +/-5g/m<sup>2</sup>)

**Weight (Before Coat):** 1.6 ounce per square yard +/- 0.06 oz/yd<sup>2</sup> (54g/m<sup>2</sup> +/-2g/m<sup>2</sup>)

**Adhesive:** Water Based Acrylic

**Mesh Size:** 9 x 9 picks per inch (6 x 6 picks per mm)

**Thickness:** 0.009 inches - .023 cm

**Warp:** 33 Tex x 2

**Weft:** 66 Tex

**Weave:** Leno

**Resin Content:** 25% +/-5%

**Tensile Strength:** Warp 57 lbs/in (500N/50mm)

Weft 57 lbs/in (550N/50mm)

**Alkaline Resistance:** After 28-day immersion in 5% Na(OH) solution, the average retention rate for tensile fracture strength:  $\geq 50\%$

**Coating:** Alkaline Resistant

10/19