



Hardcoat 20 Ounce Stucco Mesh

Weight (After Coat): 20 ounce per square yard +/- 1 oz/yd² (630g/m² +/-38g/m²)

Weight (Before Coat): 16.3 ounce per square yard +/- 0.9 oz/yd² (553g/m² +/-30g/m²)

Mesh Size: 6 x 6 picks per inch (4 x 4 picks per mm)

Thickness: 0.047 inches - .119 cm

Warp: 33 Tex x 3 x 5 x 2

Weft: 300 Tex

Weave: Leno

Resin Content: 16% +/-2%

Tensile Strength: Warp 422 lbs/in (370N/50mm)

Weft 799 lbs/in (7000N/50mm)

Alkaline Resistance: After 28-day immersion in 5% Na(OH) solution, the average retention rate for tensile fracture strength: $\geq 50\%$

Coating: Alkaline and Flame Resistant

10/19