



Impact 14 Ounce Stucco Mesh

Weight (After Coat): 14.4 oz/yd² +/- 0.44 oz/yd² (500g/m² +/-15g/m²)

Weight (Before Coat): 13 oz/yd² +/- 0.29 oz/yd² (440g/m² +/-13g/m²)

Mesh Size: 3 x 3 picks per inch (2 x 2 picks per mm)

Thickness: 0.038 inches - .097 cm

Warp: 134 Tex x 3 x 2

Weft: 2400 Tex

Weave: Leno

Resin Content: 18% +/-2%

Tensile Strength: Warp 263 lbs/in (2300N/50mm)

Weft 342 lbs/in (3000N/50mm)

Alkaline Resistance: After 28-day immersion in 5% Na(OH) solution, the average retention rate for tensile fracture strength: $\geq 50\%$

Coating: Alkaline and Flame Resistant

10/19