



Intermediate 10 Ounce Stucco Mesh

Weight (After Coat): 10 oz/yd² +/- 0.3 oz/yd² (335g/m² +/-10g/m²)

Weight (Before Coat): 8.26 oz/yd² +/- 0.24 oz/yd² (280g/m² +/-8g/m²)

Mesh Size: 6 x 6 picks per inch (4 x 4 picks per mm)

Thickness: 0.023 inches - .058 cm

Warp: 264 Tex x 2

Weft: 600 Tex

Weave: Leno

Resin Content: 18% +/-2%

Tensile Strength: Warp 228 lbs/in (2000N/50mm)

Weft 320 lbs/in (2800N/50mm)

Alkaline Resistance: After 28-day immersion in 5% Na(OH) solution, the average retention rate for tensile fracture strength: $\geq 50\%$

Coating: Alkaline and Flame Resistant

10/19