



## ***Standard 4.5 Ounce Stucco Mesh***

**Weight (After Coat):** 4.5 oz/yd<sup>2</sup> +/- 0.15 oz/yd<sup>2</sup> (153g/m<sup>2</sup> +/-5g/m<sup>2</sup>)

**Weight (Before Coat):** 3.9 oz/yd<sup>2</sup> +/- 0.06 oz/yd<sup>2</sup> (132.2g/m<sup>2</sup> +/-2g/m<sup>2</sup>)

**Mesh Size:** 6 x 6 picks per inch (4 mm x 4 mm)

**Thickness:** 0.0135 inches - .035 cm

**Warp:** 134 Tex x 2

**Weft:** 300 Tex

**Weave:** Leno

**Resin Content:** 14% ± 0.5%

**Tensile Strength:** ≥ Warp 150 lbs/in (1300N/50mm)

≥ Weft 185 lbs/in (1600N/50mm)

**Alkaline Resistance:** After 28-day immersion in 5% Na(OH) solution, the average retention rate for tensile fracture strength: ≥ 50%

**Coating:** Alkaline and Flame Resistant

10/19