

TYPAR® LIQUID FLASHING

TYPICAL CHARACTERISTICS

FOR COMMERCIAL AND RESIDENTIAL APPLICATIONS

Characteristic	Test Method	Value
Technology		Hybrid Silyl-Terminated Polyether (STPE) & Silyl Modified Polymer (SMP)
Consistency		Paste
Color		Orange
Shear Strength	ASTM D1002	130.5 psi
Tensile Strength	ASTM D412	185 psi
Elongation at Break	ASTM D412	325%
Shore A Hardness	ASTM D661	38
Initial Skin Forming Time		20 minutes
Curing Depth (Days, mm)		1 Day - 4.54 mm 3 Days - 6.19 mm 7 Days - 8.54 mm
Water Vapor Transmission Rate (WVTR)	ASTM E96 Method B, perms	14 perms @ 20 mils
Service Temperature		-40°F to 200°F (-40°C to 93°C)
Application Temperature		50°F to 180°F (10°C to 82°C)
Shelf Life		12 months in unopened containers stored between 60°F to 80°F (15°C to 26°C)
Coverage Rate		2.5 lf/oz of panel steam, 0.70 lf/oz flashing @ 12 -15 mils thickness
Voluntary Specification for Liquid-Applied Flashing Used to Create a Water-Resistive Seal Around Wall Opening in Buildings	AAMA 714-15	PASS

SIZE:	20 oz. Sausages	2-Gallon Bucket
	Sausages/Case: 12 Cases/Pallet: 90	Buckets/Pallet: 60

The information contained herein is to the best of our knowledge accurate and reliable and is provided for the user's assessment and verification. However, since the circumstances and conditions under which such information and the products discussed can be used may vary and are beyond our control. **WE MAKE NO WARRANTIES, EXPRESS OR IMPLIED, OTHER THAN THOSE WARRANTIES DESCRIBED IN THE TYPAR® WEATHER PROTECTION SYSTEM LIMITED WARRANTY LOCATED ONLINE AT [HTTP://WWW.TYPAR.COM/DOWNLOADS](http://www.typar.com/downloads), SUBJECT TO THE LIMITATIONS AND EXCLUSIONS DESCRIBED THEREIN.**



1183_0924

Made in USA. © 2025, Magnera Corporation.
TYPAR® is a trademark of Magnera Corporation or an affiliate.
Please visit [TYPAR.com](http://www.typar.com) for installation instructions and warranty information.
Building Wraps | Flashings | Construction Tape | Sealant

TYPAR®
A Magnera Brand